

*Chemical Resistance Exposure at 73°F (23°C)**

Acetic Acid up to 25%	Ferric Nitrate	Potassium Borate
Acetone (Softened)	Ferric Sulfate	Potassium Carbonate
Aluminum Chloride	Ferrous Nitrate	Potassium Chloride
Aluminum Hydroxide	Ferrous Sulfate	Potassium Dichromate up to 10%
Aluminum Nitrate	Formaldehyde up to 100%	Potassium Hydroxide
Aluminum Sulfate	Formic Acid up to 10%	Potassium Nitrate
Ammonium Carbonate	Freon, Gas & Liquid	Potassium Sulfate
Ammonium Chloride	Gas (Mfg.)	Propylene Glycol
Ammonium Hydroxide up to 100%	Gas (Natural)	Sewage
Ammonium Nitrate	Gasoline Leaded	Silver Nitrate
Ammonium Phosphate	Gasoline Unleaded	Soap Solution
Ammonium Sulfate	Glycerine	Soaps
Amyl Alcohol	Heptane	Sodium Bicarbonate
Barium Carbonate	Hexane	Sodium Bisulfate
Barium Chloride	Hexylene Glycol	Sodium Carbonate
Barium Hydroxide	Hydrochloric Acid up to 25%	Sodium Chlorate
Barium Nitrate	Hydrofluoric Acid up to 40%	Sodium Chloride
Barium Sulfate	Hydrogen Sulfide	Sodium Hydroxide
Benzene	Isopropyl Alcohol	Sodium Meta Silicate up to 5%
Boric Acid	Jet Fuel	Sodium Nitrate
Borax	Kerosene	Sodium Sulfate
Butyl Alcohol	Linseed Oil	Sodium Thiosulfate up to 50%
Cadmium Chloride	Lubricating Oil	Stannic Chloride
Cadmium Nitrate	Magnesium Carbonate	Sulfur
Cadmium Sulfate	Magnesium Chloride	Sulfuric Acid up to 60%
Calcium Carbonate	Magnesium Hydroxide	Synthetic Sea Fuel (60% Naphtha, 20% Toluene, 15% Xylene 5% Benzene)
Calcium Chloride	Magnesium Nitrate	Synthetic Silage
Calcium Hydroxide	Magnesium Sulfate	Tetraprophlene
Calcium Nitrate	MEK (Softened)	Toluene
Calcium Sulfate	Mercuric Chloride	Triethylene Glycol
Calcium Disulfide	Methanol (Softened)	Trisodium Phosphate
Carbon Tetrachloride	MIBK (Methyl Isobutyl Ketone)	Turpentine
Caustic Potash	Mineral Oil	Undecanol
Caustic Soda	Mineral Spirits	Urea
Chlorine 2%	Molasses	Urine
Citric Acid up to 25%	Motor Oil	Vinegar
Copper Chloride	Muriatic Acid	Water
Copper Nitrate	Naphtha	
Copper Sulfate	Nickel Chloride	
Crude Oil	Nickel Nitrate	

Chlorinated

Cyclohexane
Cyclohexane
Cyclopentane
Detergent
Diesel Fuel
Diethylene Glycol
Dipropylene Glycol
Ethanol (Softened)
Ethylbenzene
Ethylene Glycol
Ferric Chloride up to 50%

Nickel Sulfate
Nitric Acid up to 30%
Nonane
Octane
Oxalic Acid
Pentane
Perchloroethylene
Phosphoric Acid up to 50%
Phosphorous Trichloride
Potassium Aluminum Sulfate
Potassium Bicarbonate

Demineralized
Distilled
Salt
Sea
Xylol
Zinc Chloride
Zinc Nitrate
Zinc Sulfate
10-10-10 Fertilizer, Saturated

*Tests conducted for two years on similar products. No effect unless otherwise stated.